



versalis

www.versalis.eni.com

Technical Data Sheet

info.elastomers@versalis.eni.com

EUROPRENE[®]

BR

BR HV80

Butadiene Rubber

Europrene[®] BR HV80 is a solution polymerised high vinyl butadiene polymer produced by continuous process using an alkyl lithium catalyst at the Grangemouth production facility in Scotland, UK.
A non-staining antioxidant is added during the production process.

Main Properties	Test Method	Unit	Typical Value
Mooney Viscosity, ML 1+4(100 °C)	ASTM D 1646	MU	70
Vinyl content	Internal Method	% wt	77 ⁽¹⁾
Volatile matter	ASTM D 5668	% wt	0.8 max
Ash	ASTM D 5667	% wt	0.2 max
Tg	Internal Method	°C	-31

⁽¹⁾ Referred to butadiene portion

Key Features

Europrene[®] BR HV80 shows high rebound resilience in a wide temperature range.
It shows a unique balance of low rolling resistance and high wet grip.

Main Applications

Winter tyre tread compounds with improved wet/ice grip.

Physical Form

Water white to pale amber coloured bales wrapped in polyethylene film.

Packaging

Returnable metal crate, nominal net weight 990 kg; 33 kg bale, 30 bales per crate (1465 x 1150 x H1123 mm)

Storage Conditions

Store in a vented, dry area at temperatures between 20°C and 30°C; no direct sunlight.

Shelf life: 18 months minimum.

Please consult the relevant safety data sheet for more detailed information.

The information and data presented herein are to the best of our knowledge true and accurate, but no warranty or guarantee, expressed or implied, is made nor is any liability accepted with respect to the use of such information data.